

Material: KS STS XM-27

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and

Group: Ferrous Stainless Steel Alloys

Sub Group: KS STS XM-27 Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.400 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	25.000 - 27.500		
Molybdenum	Mo %	0.750 - 1.500		
Nickel	Ni %	0.500 max.		
Nitrogen	N %	0.015 max.		
Copper	Cu %	0.200 max.		
Ni + Cu	Ni% + Cu%	0.500 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	410 min.
-	-	-	Yield Strength in Mpa	245 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	45 min.
-	-	-	Hardness in HB	219 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44627	ASTM	USA	Steel, Plate, Sheet and Strip
S44627	UNS	USA	Steel
XM-27	SAE	USA	Steel
SUS SM-27	JIS	Japan	Steel and Bar
A276 XM-27	ASTM	USA	Steel, Bar and Shapes
A314 XM-27	ASTM	USA	Steel, Bar, Rolling and Forging
A182 F XM-27Cb	ASTM	USA	Steel, Pipe and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com