

Material: ONORM 1.0625

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: ONORM 1.0625 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 - 0.250	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.800 - 1.200		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	0.400 max.		
Molybdenum	Mo %	0.120 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.030 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 480 - 640 Yield Strength in Mpa 280 min. Elongation in % 22 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AL2	BS	British	Casting
AL3	BS	British	Casting
UC 14	ONORM	Australia	Wire and Rod
GP 280 GH	ONORM	Australia	Casting
1.0625	NBN	Belgium	Casting
GP 280 GH	NBN	Belgium	Casting
1.0625	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com