

Material: ONORM CuZn35Pb1

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: ONORM CuZn35Pb1 Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.100 max.		
Nickel	Ni %	0.300 max.		
Lead	Pb %	0.800 - 1.600		
Tin	Sn %	0.100 max.		
Other	Ot %	0.100 max.		
Copper	Cu %	62.500 - 64.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	290 - 540
-	-	-	Yield Strength in Mpa	95.2 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	61 min.
-	-	-	Hardness in HV	60 - 170
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn35Pb1	DIN	Germany	Rod
C 3501 W	JIS	Japan	Rod
CW600N	ONORM	Australia	Rod
CuZn35Pb1	EN	European Union	Rod
CW600N	EN	European Union	Rod
CuZn35Pb1	AFNOR NF	France	Rod
CW600N	AFNOR NF	France	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com