

# Material: ONORM EN 1982 CB753S

## Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ONORM EN 1982 Copper and Copper Alloys - Ingots and Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.400 - 0.800	As-Cast	
Iron	Fe %	0.500 - 0.800		
Manganese	Mn %	0.200 max.		
Nickel	Ni %	0.500 - 1.200		
Phosphorus	P %	0.020 max.		
Lead	Pb %	1.800 - 2.500		
Antimony	Sb %	0.050 max.		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.800 max.		
Cu + Ni	Cu%+Ni%	58.000 - 60.000		
Zinc	Zn %	Balance	<b>Mechanical Properties</b>	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			<b>Mechanical Properties</b>	
			Tensile Strength in Mpa	-
			Yield Strength in Mpa	-
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC753S	BS	British	Ingot and Casting
CB753S	UNI	Italy	Ingot and Casting
CB753S	UNE	Spain	Ingot and Casting
CB753S	CSN	Czech Republic	Ingot and Casting
CB753S	EN	European Union	Ingot and Casting
CB753S	DIN	Germany	Ingot and Casting
CB753S	MSZ	Hungary	Ingot and Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)