

Material: UNI CuZn40Mn1Pb1

Standard Specification for Copper and Copper Zinc Alloy Rod

Group: Non Ferrous Copper Alloys

Sub Group: UNI CuZn40Mn1Pb1 Copper and Copper Zinc Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.200 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.300 max.		
Manganese	Mn %	0.500 - 1.500		
Nickel	Ni %	0.600 max.		
Lead	Pb %	1.000 - 2.000		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.300 max.		
Other	Ot %	0.300 max.		
Copper	Cu %	57.000 - 59.000	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	350 min.
-	-	-	Yield Strength in Mpa	160 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	90 - 145
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn40Mn1Pb1	DIN	Germany	Rod
2.058	DIN	Germany	Rod
CuZn40Mn1Pb	DIN	Germany	Rod
CuZn40MnPb	DIN	Germany	Rod
SoMs58Pb	DIN	Germany	Rod
CU6	EN	European Union	Rod, Bolt, Screw, Stud and Nut
C37710	UNS	USA	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com