

## Material: UNI X 6 CrNi 23-14

## Standard Specification for Steel; Corrosion and Heat Resisting Stainless Steel Plate, Sheet, Strip and Coil

**Group:** Ferrous Stainless Steel Alloys

Sub Group: UNI X 6 CrNi 23-14 Steel; Corrosion and Heat Resisting Stainless Steel Plate, Sheet, Strip and Coil

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Plate, Sheet, Strip and Coil

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.	Solution Ann	ealing
Sulphur	S %	0.030 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	12.000 - 15.000		
Iron	Fe %	Balance		
-	•	-	Mechanical Properties	
-	-	_	Tensile Strength in Mpa	520 - 735
-	-	-	Yield Strength in Mpa	205 min.
-	1	-	Elongation in %	30 min.
-	-		Reduction of Area in %	-
-	-	-	Hardness in BHN	96 max.
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SA-351 Grade CH8	ASME	USA	Casting	
X 7 CrNi 23-14	DIN	Germany	Rolled and Forged Steel	
X 12 CrNi 23-13	EN	European Union	Bar, Wire, Strip, Plat, Sheet and Forging	
X 15 CrNi 24-13	AFNOR NF	France	Rolled Tubes for Pressure Service	
SUS 309S	JIS	Japan	Wire, Rods for Wedding Material	
309S	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging	
A351 CH8	ASTM	USA	Casting	

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



